

Phenolic Resin Analysis with Agilent PLgel Columns and Gel Permeation Chromatography

Application Note

Environmental

Introduction

Phenol formaldehyde resins are made by the reaction of phenol and formaldehyde, though precursors occasionally include other phenols or aldehydes. Phenolic resins are mainly used to make printed circuit boards, or for adhesives, coatings, and lab bench tops.

Dimethylformamide (DMF) is a polar eluent, and is therefore suitable for the analysis of polar phenolic resins. Elevated temperature is recommended to reduce operating pressures and improve resolution. Good resolution of oligomeric species is achieved using gel permeation chromatography with Agilent PLgel 5 μ m 500Å columns.

Analysis of Phenolic Resin

Two different phenolic resins were analyzed on PLgel 5 µm columns. The sample shown in Figure 1 was run on a two-column set at a lower temperature than the second sample, which was run at an elevated temperature (Figure 2). The approach adopted reflects the composition of these simple samples. For more difficult resins, Agilent PolarGel columns are recommended.



Authors

Greg Saunders and Ben MacCreath Agilent Technologies (UK) Ltd Essex Rd Church Stretton SY6 6AX UK

Conditions for Figure 1

Columns	Agilent PLgel 5 μm 500Å, 7.5 × 300 mm (p/n) PL1110-6525) Agilent PLgel 5 μm 100Å, 7.5 × 300 mm (p/n PL1110-6520)
Eluent	DMF
Flow rate	1.0 mL/min
Temp	50 °C
Detector	RI
System	Agilent PL-GPC 50



 Figure 1.
 Oligomers in a phenolic resin separated on an Agilent

 PLgel 5 μm two-column set.

Figure 2. A phenolic resin analyzed on a single Agilent PLgel 5 µm column.

Conclusion

Agilent PLgel columns in DMF can be used to investigate different samples of phenolic resin by gel permeation chromatography.

For More Information

For more information on our products and services, visit our Web site at www.agilent.com/chem.

Conditions for Figure 2

Columns	Agilent PLgel 5 µm 100Å, 7.5 × 300 mm
Eluent	DMF
Flow rate	1.0 mL/min
Temp	50 °C
Detecto:	RI
System	PL-GPC 50

www.agilent.com/chem

Agilent shall not be liable for errors contained herein or for incidental or consequential damages in connection with the furnishing, performance, or use of this material.

Information, descriptions, and specifications in this publication are subject to change without notice.

© Agilent Technologies, Inc., 2011 Printed in the USA June 29, 2011 5990-8486EN

