

Polystyrene Oligomer Analysis on Agilent PLgel with Gel Permeation Chromatography

Application Note

Materials Testing and Research, Polymers

Introduction

High performance, low pore size Agilent PLgel columns are ideal for resolving low molecular weight polystyrene standards into their oligomeric components, indicating several peaks for one standard.

Authors

Greg Saunders and Ben MacCreath Agilent Technologies (UK) Ltd Essex Rd Church Stretton SY6 6AX UK



Analysis of Polystyrene Oligomers

Structures of low molecular weight polystyrene oligomers are shown in Figure 1. The lowest MW peak can be assigned using phenyl hexane as a marker. This is styrene monomer plus the initiator fragment, with a MW of 162. Successive peaks increase in molecular weight by the MW of the styrene repeat unit, 104 (Figure 2).



Figure 1. Structures of low molecular weight polystyrene oligomers.



Figure 2. Low molecular weight oligomers of polystyrene on an Agilent PLgel 5 µm two-column set.

Conditions

Columns	2 × Agilent PLgel 5 μm 100Å, 600 × 7.5 mm (p/n PL1110-8520)
Eluent	THF
Flow rate	1.0 mL/min
Detector	RI
System	Agilent PL-GPC 50

Conclusion

High resolution GPC with low-pore-size PLgel columns can be used to resolve individual oligomers of polystyrene.

For More Information

These data represent typical results. For more information on our products and services, visit our Web site at www.agilent.com/chem.

www.agilent.com/chem

Agilent shall not be liable for errors contained herein or for incidental or consequential damages in connection with the furnishing, performance, or use of this material.

Information, descriptions, and specifications in this publication are subject to change without notice.

© Agilent Technologies, Inc., 2011 Printed in the USA May 27, 2011 5990-8323EN

