

产品说明书


Datasheet of Product

SUNRISE PAK

产品结构/Structure PET12/AD/(EVOH-EVA) 75

产品用途/Application Lidding





项目 Item		单位 Unit	标准数值 Standard Value	检测方法 Test Method
热封强度 Sealing Strength		N/15mm (190°C, 2kgf/cm ² , 1s)	≥6.0 (封PP杯)	QB/T 2358-98
剥离强度 Bond Strength	PET/EVOH- EVA	N/15mm	≥1.2	GB/T 8808-88
摩擦系数 Coefficient Of Friction			≤0.4	GB/T 10006-88
氧气透过率 OTR		cm ³ /m ² ·24hrs·0.1MPa	≤0.5	ASTMD 3985-95
水蒸气透过率 WVTR		g/m ² ·24hrs	≤0.5	ASTMF 1249-90
热封范围 Sealing Range		°C (2kgf/cm ² ,1sec)		
拉伸强度	纵向MD	N/15mm	≥40.0	GB/T 1040.3-06
断裂伸长率	纵向MD	%	≥45.0	GB/T 1040.3-06
Elongation 横向TD 残留溶剂 mg/m ²		mg/m ²	≥45.0 ≤5.0	GB/T 1040.3-06 BS 6455-1984
Tensile Strength 断裂伸长率 Elongation 残留溶剂 Residual Solvent	ensile Strength 横向TD f 裂伸长率 纵向MD % longation 横向TD k 留溶剂		≥45.0	GB/T 1040.3-06

二、产品规格指标/Product specification

卷膜尺寸偏差/Size deviation for Roll							
宽度偏差(mm) Width	厚度偏差(%) Thickness	克重偏差(%) Weight	卷长度偏差 (%)Roll length	重复单元长度偏差 (%)Repeat length	分切位置偏差(mm) Slitting		
≤±1.0	≤±10	≤±10	0~0.5	≤±0.5	≤±1.0		

成袋尺寸偏差/Size deviation for Pouch								
成袋尺寸(mm) Pouch size	厚度偏差(%) Thickness	克重偏差(%) Weight	宽度偏差 (mm)Width	长度偏差(mm) Length	封边宽度偏差(%) Sealing width			
≤100	≤±10	≤±10	≤±2.0	≤±2.0	≤±20			
100~300	≤±10	≤±10	≤±3.0	≤±3.0	≤±20			
≥300	≤±10	≤±10	≤±4.0	≤±4.0	≤±20			

三、颜色、套印(只适用于有印刷图案的产品)/Gravure printing

颜色偏差: 距印刷样1m处观察, 与标准样无明显区别。

Color:Not a sensible difference between the printing and the standard.

套印偏差: 主体部位≤±0.3mm, 其它部位≤±0.5mm。

Register:main≤±0.3mm,other≤±0.5mm.

四、卫生及理化性能指标/Hygienic standard

卫生指标符合GB 9683-1988的规定,但产品用于非食品用途品可以不要求此项。

Hygienic standard conform to GB 9683-1988, only suitable for food package.

五、运输及贮存条件/Transportation & storage condition

- 1、运输工具不能使用有异味、有污染性的车辆,运输中防止碰撞和接触锐利物体,轻装轻卸,避免日晒、雨淋,保证包装完好且产品不受污染。
- 1. Transport can't use contaminated vehicle and keep away from the collisions. Products must be pack completely and far from insolation or drench.
- 2、产品应贮存在清洁、干燥、通风、温度和相对湿度适宜的库房内,贮存温度最好在10℃~30℃,相对湿度最好在40%RH~60%RH,距热源不少于1m,不得堆放过高。
- 2. Products should be stored in a warehouse with clean,dry,ventilated,best conditions in 10~30°C and 40%rh~60%rh.Keep away from hot at least 1m and can't stack too high.
- 3、产品在符合以上规定的条件下,至生产之日起保质期为一年。
- 3. Products with the provisions of the above conditions, guaranteed for one year.

注: /Note:

- 1、以上数据均由我司实验室测试得来,因使用不同的设备、工作环境及应用场合的改变超出我们控制的范围,用户对我公司供应的产品有责任进行试验,以验证是否符合使用要求。
- 1. The above data are in our laboratory tests, for the use of various equipment and working environment and application of the change is beyond our control, the user to supply the product is responsible for the test and verify that used to meet the requirem.
- 2、本资料是产品水平的说明,未经供需双方盖章确认,不得作为产品验收标准。
- 2. Without both sides confirm, this data shall not be as a product standards.